


Appendix 8.A

Semi-annual characterization of the proctor densities of the Schuylkill Energy ash and size distribution



moisture	dry density	moisture	dry density
15.4	91.2	5.2	86.8
21.3	96.8	5.3	83.5
24.1	90.7	8.2	100.5
28.3	87.5	11.3	101.7
30.4	81.7	16.3	98.4
	11/4/98		12/4/00
20.6	87.4	7.3	97
27	89.3	10.3	98
30.1	87	12.6	99
40.9	76.4	15.4	101.5
	6/25/99	20.1	102
5.2	104.8	24	98
8.8	104.9		6/25/01
12.9	106.6	8.4	102.8
14.7	106.3	10.6	106.3
16.4	105	12.6	109.8
20	104.3	14.4	114.2
	12/7/99	15.9	112.8
16.4	83.2	17	110.5
19.6	86		7/10/01
24.8	89.4	8.4	102.9
27.6	88.9	10.6	106.5
		12.4	109.8
		14.4	114.2
		15.9	112.8
		17	110.5

seive size	7/16/01	6/1/00	1/28/00	7/8/99	12/3/98	7/17/98
0.953	99.5	99.5	100	100	98.9	99.8
0.635	99.1	99.1	99	94.3	97.2	98.2
0.254	91.9	91.9	92.1	81.8	87.6	90.6
0.025	45	45	62.2	39.2	52.2	63
0.015	11.3	11.3	49.8	7.2	30.9	34.1
0.0075	3.7	3.7	23.3	0.4	19.3	20.2

